Europa Bioproducts Ltd

15-17 North Street ● Wicken
Ely ● Cambridge ● CB7 5XW

Tel: 0044 (0)1353-721118
Fax: 0044 (0)1353-624589

Amino-EG6-undecanethiol, hydrochloride

Item#	Unit Size
A483-10	10 mg

Chemical Description: 20-(11-Mercaptoundecanyloxy)-3, 6, 9, 12, 15, 18-hexaoxaeicosane-1-amine, hydrochloride
CAS: 496839-01-1 (free base) Appearance: white or pale yellow powder Purity: ≥90.0% (HPLC, derivatization) MW: 504.16, $C_{23}H_{60}ClNO_6S$
Application: SAM preparation, amine group coating and hydrophilic surface

Storage Condition: -20ºC, protect from light and metal
Shipping Condition: ambient temperature

Product Description

Polyethyleneglycols (PEGs) are widely used for material modifications to improve hydrophilicity of the surface. PEG-coated materials are usually more stable under physiological conditions. Since Amino-EG_6-undecanethiol has 6 ethylene glycol units, 11 carbon atoms, and an SH group at the end, it can be used to prepare a highly oriented and hydrophilic SAM on a gold surface. This is suitable for biomaterial labeling on the surface due to the improved hydrophilicity. The hydrophilic surface can prevent proteins or other biomaterials from non-specific binding. Therefore, the SAM prepared by this reagent will provide a better surface to develop biomaterial sensors or DNA/ protein microarrays. To prepare an Amino-EG_6-SAM on a gold surface, hydroxy-EGn- undecanethiols (n=3, 6) are used to dilute the number of amino groups according to the density of the molecules being introduced onto the surface.

Structural Formula



CERTIFICATE NO. 32473

E.mail: info@europa-bioproducts.com
Web site: http://www.europa-bioproducts.com
Registered Office: 15-17 North Street, Wicken, Ely, Cambridgeshire CB7 5XW
Registered Number: 2703381